


# ArmaSound<sup>®</sup>

Super Silence Ductliner

HIGH PERFORMANCE ACOUSTIC  
INSULATION FOR A QUIETER  
ENVIRONMENT



- Reduces duct and plant room noise substantially
- 24x7 active anti-microbial protection for better IAQ
- Quick and easy installation - no bitumen, tissue paper or perforated sheet required
- Non- fibrous, No fiber migration
  
- Extremely high noise absorption per unit thickness
- Built-in 'Microban' protection for product lifetime
- High density to dampen duct rattling & vibration
- High Air Erosion Resistance - up to 10,000 fpm!

 **Microban<sup>®</sup>**  
antibacterial protection

# Technical Data - ArmaSound SuperSilence Ductliner

Brief description	Fibre Free, Super Silent & Microbe resistant easy to apply acoustic insulation material, with very good sound absorption, damping and barrier properties
Material type	Open cell Elastomeric foam, based on synthetic rubber (NBR)
Colour	Black
Product Range	Available in sheets, in 6 mm, 10 mm, 15 mm, 20 mm, 25 mm, 30 mm, 40 mm & 50 mm thickness . Standard Sheet size - 1 m x 1 m .
Applications	Acoustic insulation for HVAC ducts, air handling systems, plant rooms and architectural acoustics.
Special Features	Super Silent, made with Microban®* - Anti-microbial product protection, and easy to install

Property	Value/Assessment		Special Remark							
<b>Temperature Range</b>										
Temperature Range	max. service temperature	+ 85 °C								
	min. service temperature	-20 °C								
<b>Thermal Conductivity</b>										
Thermal Conductivity	$\vartheta_m$	+20	[°C]							
	$\lambda$	≤ 0.047	W/(m · K)							
<b>Fire performance</b>										
Reaction to fire	Surface spread of flames	Class 1	Tested acc. to BS 476, Part 7							
Other Fire Class	Flammability	HBF, HF-1 & HF-2 class	Tested acc. to UL 94							
Practical Fire Behavior	Self-extinguishing, does not drip and does not spread flames									
<b>Acoustic Performance</b>										
Weighted sound absorption coefficient $\alpha_w$	Practical sound absorption coefficient $\alpha_p$									
Frequency [Hz]	<b>Thickness</b>	<b>125</b>	<b>250</b>	<b>500</b>	<b>1000</b>	<b>2000</b>	<b>4000</b>			
	<b>6 mm</b>	0	0.05	0.1	0.25	0.55	1	(acc. To BS EN ISO 354:2003)		
	<b>10 mm</b>	0	0.05	0.15	0.4	0.85	1			
	<b>15 mm</b>	0	0.1	0.3	0.75	1	0.9			
	<b>20 mm</b>	0.05	0.15	0.4	0.9	1	0.95			
	<b>25 mm</b>	0.05	0.25	0.85	1	0.9	0.95			
	<b>30 mm</b>	0.1	0.35	0.95	1	0.95	1			
	<b>40 mm</b>	0.15	0.5	1	0.9	0.95	0.95			
	<b>50 mm</b>	0.25	0.75	1	1	1	1			
		<b>Thickness</b>	<b>6 mm</b>	<b>10 mm</b>	<b>15 mm</b>	<b>20 mm</b>	<b>25 mm</b>	<b>30 mm</b>	<b>40 mm</b>	<b>50 mm</b>
	$\alpha_w$	0.2	0.25	0.35	0.4	0.55	0.65	0.8	1	
	Class	E	E	D	D	D	C	B	A	(acc. To EN ISO 11654:1997)
	NRC	0.2	0.35	0.55	0.6	0.8	0.85	0.85	1.05	(acc. To ASTM C 423)
Density	140-180 Kg/m <sup>3</sup>									
UV resistance	Shall be protected from direct Sunlight. For outdoors Arma-Chek coverings systems shall be applied, within 2 days of installation.									
Health aspects	Dust & Fibre free									
Storage & Shelf life	Shall be stored away from direct Sunlight									
Antimicrobial behaviour	In-built Microban® active antimicrobial protection: No fungal & bacterial growth								Tested acc. to ASTM G 21 & ASTM E 2180	
Air Erosion Resistance	No erosion, cracking or delamination at air velocity of 10,000 fpm								Tested acc. to ASTM C 1071-05	

\*Microban is EPA (Environment Protection Agency), USA Approved.

All data and technical information are based on results achieved under typical application conditions. Recipients of this information should, in their own interest and responsibility, clarify with us in due time whether or not the data and information apply to the intended application area. Installation instructions are available in our ArmaSound installation manual.

## Armacell (Thailand) Limited

88 Mu 4, Donkrabueng • 70110 Banpong • Ratchaburi 70110 • Thailand  
Phone +66 (0) 32 353 205-7 • Fax +66 (0) 32 353 208  
www.armacell.com • info.thailand@armacell.com

## Armacell Asia Limited (Singapore Branch)

Singapore Branch 391B Orchard Road • #23-01 Ngee Ann City • Tower B • Singapore  
Phone +65 9720 3409 • Fax +65 6832 8018  
www.armacell.com • info.singapore@armacell.com

## Armacell Asia Limited (Vietnam Representative Office)

266/22 Street TA28 Ward Thoi An, District 12 • Ho Chi Minh City • Vietnam  
Phone +84-8-6674 1098 • Fax +84-8-6250 7339  
www.armacell.com • info.vietnam@armacell.com

## Armacell Asia Ltd. (Indonesia Representative Office)

Menara Karya, 28th Floor Jl. H.R. Rasuna Said Block X-5 Kav. • 12950 1-2 Jakarta • Indonesia  
Phone +62 21 5789 5568 • Fax +62 21 5789 5888  
www.armacell.com • info.indonesia@armacell.com

## Armacell Asia Limited (Philippines Representative Office)

5/F Builder's Center • 170 Salcedo St. • Legaspi Village • Makati City 1229 • Philippines  
Phone +63 2902 0956 • Fax +63 2902 0949  
www.armacell.com • info.phillippines@armacell.com

IPRN-0131-130809-en(TH, ID, VN, PH)



© Armacell Enterprise GmbH & Co. KG